



<b>*** PROJECT INFORMATION ***</b>			
Customer:	ILPO SRL		
Order Number:	KUEXT12414	Lot Number:	Ilpotech
Date Received:	17.07.2018	Material Type:	-
Date Tested:	25.07.2018	Batch:	-
Project Number:	-	File Number:	-
-			

<b>*** SAMPLE SET INFORMATION TABLE ***</b>			
Nom. Thickness [mm]	4.5	Color:	Black
Nom. Cond. Time [hrs]	Nom. Cond. Temp [°C]	Rating	Tested by:
48	23	V-0	48809, ULBAJ
168	70	V-0	21935, ULHOI
Overall Rating:		V-0	
Cmts	48 [hrs]		
Cmts	168 [hrs]		

<b>*** TEST PARAMETERS INFORMATION ***</b>	
t1:	Afterflame time after first application
t2:	Afterflame time after second application
t2+t3:	Afterflame time plus Afterglow time after second application
tf(1-5):	Total flame time. Sum(t1i + t2i), i from 1 to 5
tf(6-10):	Total flame time. Sum(t1i + t2i), i from 6 to 10
Cmts X1:	Comments for first application
Cmts X2:	Comments for second application

<b>*** COMMENTS TABLE ***</b>	
Number	Description
1	Specimen burned up to holding clamp
2	Specimen did NOT drip
3	Specimen dripped particles, which did NOT ignite cotton
4	Specimen dripped particles, which IGNITED cotton
5	Fumes from specimen extinguished flame. Burner relit during test
6	Specimen burned to holding clamp after 1st application
7	Cotton consumed after 1st application
8	Afterflame time exceeds 35 seconds – test terminated.
9	Other

<b>*** MISCE. MEASUREMENTS ***</b>		
MeasurementName	Measurement Value	
	48h/23°C	168h/70°C
Ambient Temperature [°C]	23,2	23,4
Ambient Humidity [%RH]	54	55,6
Cotton Desicator Temperature [°C]	23,2	23,4
Cotton Desicator Humidity [%RH]	< 20	< 20