

TEST REPORT

352630 / 1

Revision: 0
Date of sample receipt: 27/06/23
Date of test: 18/07/23
Date of issue: 18/07/23

Sample name: ILPOFLEX 1IM

ILPO S.R.L.
VIA FRIULI 1-3 - OSTERIA GRANDE
40024 CASTEL SAN PIETRO TERME (BO)
ITALIA

Small flame applied only on upholstery filling UNI 9175:2010

Description of materials as declared by the client

Cover material: none.

Filling material: polyurethane foam "ILPOFLEX 1IM" of ILPO SRL Company, density 60 g/l.

End use: upholstered furniture.

Deviations from the standard as requested by the client

None.

Preliminaries

Sampling procedure: performed by the client.

Conditioning

Filling material: 72 hours at 80 ± 5 °C and 80 ± 5 % relative humidity following a minimum of 48 hours at 23 ± 2 °C and 50 ± 5 % relative humidity.

Test results:

Materials tested	Tests	Test results according to ignition source times								
		20 s	tpc (s)	tpi (s)	80 s	tpc (s)	tpi (s)	140 s	tpc (s)	tpi (s)
Filling material	1st	Pass	0	0						
	2nd	Pass	0	0						
Filling material	1st	Pass	0	0	Pass	0	0	Pass	0	0
	2nd	Pass	0	0	Pass	0	0	Pass	0	0
	3rd	=			=			=		

Notes: /


tpc: post-combustion time.

tpi: post-incandescence time.

Based on test results, the sample examined complies with class 1.IM (ONE I M).

This test report is not issued according to articles 8 and 10 of D.M. 26-06-1984 amended by D.M. 03-09-2001.

This test report is part of a PDF file digitally signed by Franco Bulian.

*The managing director
Dr. Franco Bulian*


The sample name and, when relevant, its description, are given by the orderer, and CATAS does not assume responsibility on this matter. This test report relates to the sample submitted for the test and no others. Additions, deletions or alterations are not permitted. This test report must always be reproduced in its entirety. Unless otherwise required by standards and technical specifications or agreed with the customer, any declarations of conformity made by CATAS are based on the comparison between results and reference values, where the confidence intervals of the measures are not taken into account. Unless otherwise stated, sampling is made by the customer; in this case the test results are referred to the sample as received.